

Hess Grade 230 LHM (LD)

ISSUE 6/2004
REVISION N/A
REVIEW 1/2008

PARTICLE SIZE SPECIFICATION GRADE 230 LHM (LD)

Laser Diffraction Analysis	Allowable Range (Microns)
D90	62-80
D75	49-60
D50	32-42
D25	15-25
D10	3-9
Mean	33-45
Median	31-43

TEST METHOD: Refer to Standard Method

LOOSE BULK DENSITY GRADE 230 LHM (LD)

44 lbs/per cubic foot (ASTM C29)

CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

TYPICAL ANALYSIS

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%
- Crystalline SiO₂: None Detected

GENERAL PROPERTIES

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition - 5%
- GE Brightness: 84
- Specific Gravity: 2.35
- Reactivity: Inert
(except in the presence of calcium hydroxide or hydrofluoric acid)

DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

GRADE APPLICATIONS

Used for: glass cleaner.

PACKAGING OPTIONS

- 45 lb sacks (palletted)
- 2000 lb super sacks (palletted)
- Bulk shipped in pneumatic rail car or tractor trailer

DISTRIBUTOR NETWORK

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.



Hess | **PUMICE**
IDAHO USA

(208) 766-4777 x111 • email: rd@hesspumice.com
www.hesspumice.com