

# Hess Grade 6/0N

ISSUE 2000  
 REVISION 4/2001  
 REVIEW 3/2016

## PARTICLE SIZE SPECIFICATION GRADE 6/0N

SIZE		ALLOWABLE PERCENT PASSING
MICRON/MM	U.S. MESH	
106/0.106	140	100
90/0.090	170	99-100
75/0.075	200	95-100
63/0.063	230	86-98
45/0.045	325	55-65

TEST METHOD: ASTM C136-06

## LOOSE BULK DENSITY GRADE 6/0N

**832.9** kgs/per cubic meter (ASTM C29)

## CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

**Chemical Name:** Amorphous Aluminum Silicate

### TYPICAL ANALYSIS

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%
- Crystalline SiO<sub>2</sub>: None Detected

### GENERAL PROPERTIES

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition - 5%
- GE Brightness: 84
- Specific Gravity: 2.35
- Reactivity: Inert  
(except in the presence of calcium hydroxide or hydrofluoric acid)

## DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

## GRADE APPLICATIONS

Used for: plastics tumbling.

## PACKAGING OPTIONS

- 18 kg sacks (palletted)
- 907 kg super sacks (palletted)
- Bulk shipped in pneumatic rail car or tractor trailer

## DISTRIBUTOR NETWORK

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.



**Hess** | **PUMICE**  
 IDAHO USA

(208) 766-4777 x111 • email: rd@hesspumice.com  
 www.hesspumice.com

*Mining and refining the purest commercial deposit of white pumice on the planet.*